



Product Data Sheet

PROVAP Primer

Product Characteristics	
Characteristics	Value
Appearance	Red liquid
Viscosity	150cp @ 20°C
Solids	28%
Specific Gravity	1.25
Flash Point	Although a quantity of a flammable material is present, this preparation is non flammable as supplied
Shelf Life	12 months unopened
Storage Temperature	Between 5°C - 25°C
Temperature for use	+5°C - rising



Product Description

A rapid drying primer made with SBS resins and non flammable solvent.

Chemical Composition

Non flammable solvent based SBS adhesive primer.

Applications

PROVAP Primer is designed for use with PROVAP S/A and modified bitumen roofing membranes and is intended for use on concrete and various porous substrates to aid initial and long term adhesion of the membrane particularly when application is taking place at the lower end of the temperature range (+5°c).

Recommendations for use

- For best results ensure that surface to be primed is free from oil ordust
- Wash or sweep clean where necessary
- Apply thinly with roller in one sweep (the red colour will denote area treated)- refill roller if "cobwebbing" occurs.
- Avoid puddling of the primer.
- Drying time will be affected by surface porosity, film thickness and temperature and can vary between 40-90 minutes.

• Product will remain tacky even after dry. To test, using the back of a glove or dry object press into the primer and remove, there should be no transfer of the primer when the primer is ready.

Substrate	Typical Coverage RedStar Primer
Concrete (subject to type, quality and porosity)	7 m²
Plywood / OSB	8-9 m²
Metal	10 m²

Packaging

5 ltr metal cans with pour spout. 15 ltr cans available on request.

Health & Safety

Wear protective clothing, gloves and eyewear For use as a surface primer, do not use in poorly ventilated areas. Refer to Material Safety Data sheet before handling or use.

NOTE: It is essential that sufficient drying time is allowed as any entrapment of solvent will result in blistering/delamination. Only prime areas that will be covered within 2-3 hours. Avoid walking over, as far as practical, areas already primed.

CE Declaration of Performance is available on request



This information given in good faith and is based on the latest knowledge available to Rubberseal Ltd. Whilst every effort has been made to ensure that the contents of the publication are current while going to press, customers are advised that products, techniques and codes of practice are under constant review and liable to change without notice.